



POLITERM® BLU FEIN

**SUPERLIGHT THERMAL INSULATING AGGREGATE, WITH FINE GRAIN,
FOR THE PREPARATION OF LIGHTWEIGHT MORTARS FOR SCREEDS**

POLITERM® BLU FEIN

Superlight thermal insulating aggregate, with fine grain, for the preparation of lightweight mortars for screeds

COMPOSITION	Expanded virgin close-cell polystyrene beads with fine grain (\varnothing 5/64"), perfectly spherical, controlled density, non-toxic, non-absorbent, rotproof, dimensionally stable over time, free of chlorofluorocarbon (CFC, HCFC and HFC) and nutritional values able to sustain growth of fungi and bacteria. In the production phase, the beads are mixed with the special E.I.A. additive which allows a perfect mixing with the water binder, eliminates the bead floating phenomenon and guarantees their homogeneous distribution in the mix.
PACKAGING AND STORAGE	<ul style="list-style-type: none"> · Bag of 444 qt (n° 2 bags = 35.3 ft³ of finished mortar). · Bag of 180 qt (n° 5 bags = 35.3 ft³ of finished mortar). · Keep the product away from water and humidity. Store the product in the original closed packaging. Store the material in a dry, well-ventilated place, away from frost, heat sources and direct sunlight.
FIELDS OF APPLICATION	<ul style="list-style-type: none"> · Base screeds for basements and pilotis floors, space between floors, roofs and wooden floors. · Single-layer screeds for direct gluing of floor finishings, basements, pilotis floors, space between floors, roofs and wooden floors (consult "Politerm® Blu Application Manual"). · Formation of gradients on terraces and flat roofs, also with following direct laying of waterproofing membrane (prefabricated: hot or cold, synthetic bituminous - liquids: provided that solvents are not present). · Insulation of unwalkable attics. · Insulation of pitched roofs, also with following direct laying of waterproofing membrane (prefabricated: hot or cold, synthetic bituminous - liquids: provided that solvents are not present). · Filling of vaults, even highly thick. · Encapsulation of asbestos cement fibre sheets roofs, also with following direct laying of waterproofing membrane (prefabricated: hot or cold, synthetic bituminous - liquids: provided that solvents are not present). · Filling beneath trafficable asphalt pavements. · Beneath industrial flooring.
CONSUMPTION / YIELD	<p>35.3 ft³ of finished mortar is obtained with:</p> <ul style="list-style-type: none"> · N° 2 bags of 444 qt of Politerm® Blu Fein + water + cement * · N° 5 bags of 180 qt of Politerm® Blu Fein + water + cement * <p>* see prescribed dosages.</p>
PREPARATION OF THE LAYING SURFACE	<p>The laying surface must always be clean and free of dust and fragments of any kind.</p> <ul style="list-style-type: none"> · Cement and brick-cement laying surfaces or absorbent surfaces: abundantly wet the surface, without leaving puddles. · Poorly absorbent laying surfaces (very dense cement surfaces, etc.): treat the laying surface with adhesion promoter (type Edilstik) before casting the mortar prepared with Politerm® Blu Fein and work fresh on fresh, or make an adhesion bridge with cement grout hydrated with water and Edilstik, or use a suitable anchorage primer. · Non-absorbent laying surfaces (sheaths, metal, ceramic, insulating sheets, etc.): apply a galvanized mesh \varnothing 5/64" - 19 11/16 x 19 11/16 in (to a third of the final thickness of the casting to be realized), before the laying of Politerm® Blu Fein. · Single-layer screeds for direct gluing of floor coverings: it is recommended to lay some special PVC guides called Piano Zero beforehand.



Thermal Insulation & Chemicals Division



Edilteco S.p.A. Via dell'Industria, 710 - 41038 San Felice sul Panaro (MO) Italy
Ph. +39 0535 82161 . Fax +39 0535 82970 . www.edilteco.com | info@edilteco.com

© Copyright EDILTECO S.p.A. - Non authorized reproduction is forbidden.



Use only CEM I or CEM II Portland 32.5/42.5/52.5 concrete and in perfect conservation conditions, according to the law. Different types or poor-quality concrete may affect the functionality of E.I.A. additive which is added to Politerm® Blu Fein beads. It would make the mixing difficult and the final properties of the mortar not compliant.

Dosages to obtain 35.3 ft³ of lightweight thermal insulating mortar:

FORMULA	BAGS POLITERM® BLU FEIN	WATER qt °	CEMENT lb	SAND lb *
110 - 6.86	444 qt: n° 2 or 180 qt: n° 5	53	242.5	not necessary
200 - 12.49		95	440.9	
250 - 15.60		116	551.2	
300 - 18.73		148	661.4	
350 - 21.84		169	771.6	
500 - 31.21		148	661.4	352.7
800 - 49.94	719 qt	148	661.4	992.1

Dosages to obtain 7,12 ft³ (211 qt) of lightweight thermal insulating mortar (e.g.: mixing in cement mixer):

FORMULA	BAGS POLITERM® BLU FEIN	WATER qt °	CEMENT lb	SAND lb *
110 - 6.86	180 qt: n° 1	11	48.2	not necessary
200 - 12.49		19	88.2	
250 - 15.60		23	110.2	
300 - 18.73		30	132.3	
350 - 21.84		34	154.3	
500 - 31.21		30	66.1	70.5
800 - 49.94	143 qt	30	66.1	198.4

* Sand is not necessary thanks to the mixing properties of Politerm® Blu Fein. Sand may however be used being aware of the fact that it reduces performance in terms of lightening, thermal insulation and water retention. If using sand the water dosages will vary depending on the amount of sand and its residual moisture. Sand may have to be used when utilizing pumps type "Turbosol" for sand and cement screeds.

MIXING AND APPLICATION

- **Mixing:** the mortars prepared with Politerm® Blu Fein can be mixed with:
 - Cement mixer.
 - Horizontal mixer.
- **Mixing and pumping:** the mortars prepared with Politerm® Blu Fein can be mixed and pumped on site with:
 - Specific equipment type Politerm® Machine and/or Isolcap Machine *[see Edilteco equipment]*.
 - Pumps type "Turbosol" for sand and cement screeds *[contact the Edilteco Technical Department]*.
- **Order of component infeed with Politerm® Machine:**
 1. Switch on the mixer;
 2. Insert the needed water according to the formulation;
 3. Insert the content of 1 bag of Politerm® Blu Fein;
 4. Insert the necessary amount of cement;
 5. Insert the second bag of Politerm® Blu Fein;
 6. Mix for 10 minutes (loading time included) before pumping.
- **Use of antifreeze:** at temperatures below 41 °F, it is recommended to add liquid antifreeze to the dosages recommended by the manufacturer. Any use of antifreeze additives is compatible with the physical-chemical properties of Politerm® Blu Fein.
- **Single-layer screeds for direct gluing of floor coverings:** consult the "Politerm® Blu Application Manual" or contact the *Edilteco Technical Department*.

WARNINGS

- Do not apply with temperatures inferior than 41 °F or under the direct sunlight or with temperatures higher than 95 °F. If the application is made under the direct sunlight, necessary precautions must be taken (e.g. mesh or similar that covers the scaffolding).
- It is recommended to lay edge strips of acoustic insulation wider than the floor covering
- **Minimum thickness:**
 - a) *Absorbent surface:* 2". In case of sub-thickness consult the "Politerm® Blu Application Manual" or contact the *Edilteco Technical Department*.
 - b) *Non-absorbent surface:* consult the "Politerm® Blu Application Manual" or contact the *Edilteco Technical Department*.



Thermal Insulation & Chemicals Division



Edilteco S.p.A. Via dell'Industria, 710 . 41038 San Felice sul Panaro (MO) Italy
Ph. +39 0535 82161 . Fax +39 0535 82970 . www.edilteco.com | info@edilteco.com



TECHNICAL CHARACTERISTICS	CHARACTERISTICS	FORMULA						
		110 - 6.86	200 - 12.49	250 - 15.60	300 - 18.73	350 - 21.84	500 - 31.21	800 - 49.94
	Density after 28 days lb/ft ³ :	~ 8.12 ^(a)	~ 13.42	~ 16.54	~ 19.66	~ 22.79	~ 32.15	~ 50.88
	Thermal conductivity λ_D W/mK:	0,043	0,065	0,067	0,080	0,103	0,104	0,176
	Compressive strength psi:	77	100	120	234	245	325	580
	Flexural strength psi:	17	54	67	138	85	113	145
	Cohesion psi:	n.a.	12	n.a.	18	n.a.	n.a.	n.a.
	Hot-sealed membrane rupture N/50 mm:	n.a.	57	n.a.	62	21,28	n.a.	n.a.
	Cold-sealed membrane rupture N/50 mm:	n.a.	35	n.a.	47	13,00	n.a.	n.a.
	Elasticity module ksi:	n.a.	34	n.a.	80	n.a.	n.a.	n.a.
	Permeability to water vapour μ :	5,1	5,9	6,9	7,2	9,2	10,2	14,0
	Specific heat kJ/kgK:	1,4	1,4	1,4	1,4	1,4	1,4	1,4
	Shrinkage (NBN) mm/m:	n.a.	0,427	n.a.	0,352	0,270	n.a.	n.a.
	Acoustic performance ΔL_w :	n.a.	n.a.	14 dB *	26 dB **	n.a.	17 dB	19 dB
	Impact noise insulation $L'_{nT,W}$:	n.a.	n.a.	61 dB thick. 4"+3/8"	n.a.	n.a.	n.a.	n.a.
	Fire reactivity class:	A2-s1,d0						

All the indications provided in this technical data sheet are purely approximate and not binding for legal purpose. The data listed has been gathered from laboratory tests and it hence follows that in practical applications on building sites the final characteristics of the products may be subject to substantial variations depending on the meteorological conditions and the installation. The user must always check suitability of the product for its specific use, undertaking all liability implicit in and deriving from use of the product, as well as comply with all methods and instructions for use generally referable to "workmanlike" execution. Edilteco S.p.A. reserves the right to change the contents of this mechanical data sheet on its final judgements. The spreading of this data sheet through any media, supersedes and cancels the validity of any other technical data sheet previously published.

^(a) Only with **Politerm® Blu Fein**. For methods and application contact the Edilteco Technical Department.
* Value obtained in laboratory with 2" of Politerm® Blu Fein + 2" of screed / ** Value obtained in laboratory with 1"+3/4" of Politerm® Blu Fein + Fonotech 5.

DETERMINATION OF THE THERMAL RESISTANCE "R" * VALUE

According to the application thickness (lightweight screeds and base screeds)

FORMULA	THERMAL CONDUCTIVITY λ_D W/mK	COEFFICIENT	THICKNESS	
			1 31/32 in [5 cm]	3 15/16 in [10 cm]
110 - 6.86	0,043	R m^2k/W $=$ $(\text{thickness}/\lambda)$	1,16	2,33
200 - 12.49	0,065		0,77	1,54
250 - 15.60	0,067		0,75	1,49
300 - 18.73	0,080		0,63	1,25
350 - 21.84	0,103		0,48	0,97
500 - 31.21	0,104		0,48	0,96
800 - 49.94	0,176		0,28	0,57
(*) Ref. λ_D				

LEED CRITERIA		
SECTIONS	CREDITS	TECHNICAL DESCRIPTIONS
Energy and Atmosphere (EA)	Prerequisite 2	Minimum energetic performances
	Credit 1	Optimization of the energy performances
Materials and Resources (MR)	Credit 5	Extracted, processed and produced at a limited distance materials (regional materials)



Thermal Insulation & Chemicals Division

DS POLITERM® BLU FEIN . Rev 10/2022 . GB USA



Edilteco S.p.A. Via dell'Industria, 710 . 41038 San Felice sul Panaro (MO) Italy
Ph. +39 0535 82161 . Fax +39 0535 82970 . www.edilteco.com | info@edilteco.com



© Copyright EDILTECO S.p.A. - Non authorized reproduction is forbidden.